

abrasive blasting cabinet gloves

Specifications :

Price	Contact Us
Place of Origin	Shandong, China
Payment Terms	T/T, L/C, Western Union, etc.
Delivery Detail	10-25 Working Days.
Keyword	Sandblasting Gloves

Detail Introduction :

Product Description

Product Description



Product Parameters

Items of inspection	Standard	Test result
Material	Natural Rubber	Qualified

Appearance Quality	No obvious particle(?0.5%), Crocking, Fragility, Stickiness	Qualified
	No obvious color aberration	Qualified
No Leakage	No Leakage Under10±1kPa	No Leakage
Tensile Strength	?19.6Mpa	28.8Mpa
Elongation At Break	700%	730%
Permanent Deformation At Break	?12%	10%
Tensile Strength After Acid Treatment	?17.6Mpa	21Mpa
Elongation At Break After Acid Treatment	?650%	670%
Tensile Strength After Alkaline Treatment	?17.6Mpa	21Mpa
Elongation At Break After Alkaline Treatment	?650%	670%

Product Details



Certifications

