

Silver Bright Color Steel Grit - steel grit g40 High Carbon Steel Grit For Abrasive Refractory Industry

Specifications :

| | |
|-----------------|-------------------------------|
| Price | Contact Us |
| Place of Origin | Shandong, China |
| Payment Terms | T/T, L/C, Western Union, etc. |
| Delivery Detail | 10-25 Working Days. |
| Keyword | Steel Grit Blasting Media |

Detail Introduction :

Steel Grit - High carbon steel grit

Three types of grits as below:

- 1) GP grits with normal hardness ranging from 42-50 HRC. The edges diminish with time.
- 2) GL grits with hardness ranging from 50-60 HRC. The edges diminish with time and become round after few operations.
- 3) GH grits with hardness ranging from 60-66 HRC. Used for marble & granite cuttings and finishing. Being hardened, the edges remain sharp throughout the process and for a longer time.

Specification:

| | | |
|------------------------------|-------------------------------|-----------|
| Product | STEEL GRIT GH/GL/GP10-120 | |
| Chemical Composition % | C | 0.85-1.20 |
| | Mn | 0.40-1.20 |
| | Si | 0.40-1.20 |
| | S | ≤0.05 |
| | P | ≤0.05 |
| Hardness (HRC) | 60-66(GH) 50-60(GL) 42-50(GP) | |
| Density (g/cm ³) | 7.4 | |
| Metallographic Structure | Even tempered martensite | |