

zinc alloy beads

Specifications:

epoomounono :		
Price	Contact Us	
Place of Origin	Shandong, China	
Payment Terms	T/T, L/C, Western Union, etc.	
Delivery Detail	10-25 Working Days.	
Keyword	Zinc Shot	

Detail Introduction:

Zinc cut wire shot - As Cut or Conditioned

Appearance is bright. The density of zinc shot is higher than aluminum, hardness softer than steel, then it can deburr products without wearing down the surface. Widely used for deburring and surface treatment of zinc and aluminum cast parts.

Chemical composition of zinc shot

Droduct	Grade	Chemical composition (%)					Donoity	Hardnaga
Product Grad	Product Grade	Zn	Fe	Al	Cu	Co	Density	Hardness
Zinc cut wire shot - G3 Conditioned	0#Zn	99.99%	0.004%	0.003%	0.001%	0.003%	7.1g/cm ³	45-60HV
Zinc cut wire shot - As Cut	0#Zn	99.99%	0.004%	0.003%	0.001%	0.003%		35-55HV

Size Available:

0.6, 0.8, 1.0, 1.2, 1.5, 1.7, 2.0, 2.3, 2.5, 3.0 mm

Our Company:

Zibo Yalong Abrasive Co., Ltd, established in 2007, based in Zibo City, Shandong Province, is a leading manufacturer of metallic abrasives. We produce high quality Steel Shot, Steel Grit, Steel Cut Wire Shot, Stainless Steel Cut Wire Shot etc.





Packing:







