

zinc wire shot

Specifications :

Price	Contact Us
Place of Origin	Shandong, China
Payment Terms	T/T, L/C, Western Union, etc.
Delivery Detail	10-25 Working Days.
Keyword	Zinc Shot

Detail Introduction :

Zinc cut wire shot - As Cut or Conditioned

Appearance is bright. The density of zinc shot is higher than aluminum, hardness softer than steel, then it can deburr products without wearing down the surface. Widely used for deburring and surface treatment of zinc and aluminum cast parts.

Chemical composition of zinc shot

Product	Grade	Chemical composition (%)					Density	Hardness
		Zn	Fe	Al	Cu	Co		
Zinc cut wire shot - G3 Conditioned	0#Zn	99.99%	0.004%	0.003%	0.001%	0.003%	7.1g/cm ³	45-60HV
Zinc cut wire shot - As Cut	0#Zn	99.99%	0.004%	0.003%	0.001%	0.003%		35-55HV

Size Available:

0.6, 0.8, 1.0, 1.2, 1.5, 1.7, 2.0, 2.3, 2.5, 3.0 mm

Application

marin
shipbuilding



aerospace



Marine engineering
equipment



rail transit



construction
engineering



human body
implant



life appliance



electrical power
equipment

